Scotch[®] Tear Tape 8626

Product Description	Scotch [®] Tear Tape 8626 is designed for use as the easy-opening device on medium- to heavy-weight corrugated fiberboard packaging materials. Typical easy-opening applications for Scotch [®] Tape 8626 include: overnight courier boxes; audio/video/ CD/book mailers; printed boxes used in the retail market for such items as electronics, toys, medical, computers, and clothing; and shipping boxes used by catalogs and "mail order" retailers, who want to avoid product damage from knives razor blades and scissors used to open the packages.			
Construction	Backing	Adhesive	Reinforcement	Backing Colo
	Tensilized polypropylene	Pressure sensitive synthetic rubber res	None	lvory
Typical Physical	Note: The following tec			
Typical Physical Properties*	or typical only, a	nd should not be used	for specification purpo	ses. ASTM Test Metho
	or typical only, a	nd should not be used 75 oz./in. width (82 N	for specification purpo	ses. ASTM Test Metho D-3330
	or typical only, a Adhesion to Steel: Tensile Strength:	nd should not be used 75 oz./in. width (82 N 220 lbs./in. width (38	for specification purpo	ses. ASTM Test Metho D-3330 D-3759
	or typical only, a	nd should not be used 75 oz./in. width (82 N	for specification purpo	ses. ASTM Test Metho D-3330
	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break:	nd should not be used 75 oz./in. width (82 N 220 lbs./in. width (38 30% 6.2 mil (.157 mm)	for specification purpo	ASTM Test Metho D-3330 D-3759 D-3759 D-3652
	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break: Total Thickness:	nd should not be used 75 oz./in. width (82 N 220 lbs./in. width (38 30% 6.2 mil (.157 mm) n. As sufficient production	for specification purpo	ASTM Test Metho D-3330 D-3759 D-3759 D-3652
Properties*	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break: Total Thickness: *Based on limited production Available Widths	nd should not be used 75 oz./in. width (82 N 220 lbs./in. width (38 30% 6.2 mil (.157 mm) n. As sufficient production	for specification purpo	ASTM Test Metho D-3330 D-3759 D-3759 D-3652 lata sheet will be issue
Properties*	or typical only, a Adhesion to Steel: Tensile Strength: Elongation at Break: Total Thickness: *Based on limited production Available Widths Standard Widths: .1875	nd should not be used 75 oz./in. width (82 N 220 lbs./in. width (38 30% 6.2 mil (.157 mm) n. As sufficient production	for specification purpo	ASTM Test Metho D-3330 D-3759 D-3759 D-3652 Iata sheet will be issue

Storage Conditions

Store behind present stock. Store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40-50% relative humidity are recommended. Rotate your stock.

Scotch[®] Tear Tape

8626

For Additional Information	To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/packaging. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.
Important Notice	3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's application.
Limitation of Remedies and Liability	If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.



Industrial Business Industrial Adhesives and Tapes Division 3M Center, Building 21-1W-10, 900 Bush Avenue St. Paul, MN 55144-1000



Recycled Paper 40% pre-consumer 10% post-consumer